

FPM 70 / 80-01-70052

70 ShA / bisphenolic crosslinked / FDA / black

- Fluorinated rubber
- Type A (approx. 66% fluorine)
- Specification according to FDA
- Very good temperature resistance, high chemical resistance.
- Excellent resistance to ozone, ageing and weathering.

Property	Value	Unit	DIN Standard
Hardness	70 ±5	Shore A	DIN ISO 7619-1
Density	1,84 ±0,03	g/cm ³	DIN EN ISO 1183-1A
Elongation at break	239	%	DIN 53504
Tensile strength	12,6	N/mm ²	DIN 53504
Compression set 150°C/24h	8,4	%	DIN ISO 815
Rebound resilience	6	%	DIN ISO 53512
Tear resistance	6,2	N/mm	DIN ISO 34-1 A
Tear resistance	11,1	N/mm	DIN ISO 34-1 B
TR 10	-18	°C	–
min. operating temperature static	-25	°C	in the cold
max. operating temperature	+230	°C	constantly
max. operating temperature short	+275	°C	couple of hours
Specification	FDA compliant		

FDA confirmation

We hereby confirm that our quality 80-01-70052 FPM 70 black, complies with FDA - Code of Federal Regulation, Title 21 (CFR 21), Section 177.2600, "Rubber Articles Intended for Repeated Use", status 01.04.2005 and therefore may be used for the production of articles which are in short-term contact with food.

BfR XXI Commodity articles based on natural and synthetic rubber, status 01.02.2005; Category 4

Conformity with REGULATION (EC) No 1935/2004

Since due to technically unavoidable conditions or delivery forms of the raw materials, the elastomermixtures contain traces of substances not listed in these recommendations and guidelines. In any case, the prescribed tests shall be carried out on the finished part.

All above stated data result from random tests which were taken from the ongoing production. All data were established based on standard test-specimen according to ISO, DIN and ASTM standards and can basically not be carried over to the construction element.

Our applied technical advice, either oral, written or through tests is given according to our best knowledge. However, this information is to be considered as non-obligatory instruction, also in terms of any protective rights of a third party, and does not exempt you from testing our product in reference to its suitability for the intended process and purpose. Utilisation, application and processing of the products occur entirely outside of our control and are therefore exclusively your responsibility. However, should a case of liability come into question, it will be limited to all damages in the value of the product which we delivered and you used. By all means, we do warrant the impeccable quality of our products in accordance with our general sales and delivery conditions.